

## PETMET 180HB

_	
Features:	
realures.	

- High optical density
- Good flex crack resistance
  Outstanding metal adhesion is
  - Outstanding metal adhesion is obtained by metallization on special chemical coated layer
- Exceptional barrier properties against to oxygen and water vapor, to preserve flavor, taste and freshness

Aluminum Layer Chemical Coated BOPET Layer BOPET core Layer BOPET Layer

Application:

.

High barrier metallized film used for flexible packaging; specifically designed for hot filling, sterilization and pasteurization processes.

Specification	Test Method	Unit	Test Direction	8μ	10μ	12μ	18μ	23μ	36µ
Yield	ASTM D4321	m²/Kg	-	89.3	71.4	59.5	39.6	31.1	19.8
Wetting Tension	ASTM D2578	Dyne/cm	Metal Side	60					
Tensile Strength	ASTM D882	N/mm²	MD	180			190		
			TD	190			200		
Elongation at Break	ASTM D882	%	MD	130		135			
			TD	120		125			
Thermal Shrinkage (150 °C, 30 min)	ASTM D1204	%	MD	2		1.5			
	A31101 D1204		TD		1		0.5		
Metal Bond Strength	AIMCAL	gr/25 mm	-	850					
Optical Density	Gretag	-	-	2					
Dynamic C.O.F	ASTM D1894	-	-	0.5					
WVTR (38° C , 90% RH)	ASTM F1249	g/m²/day	-	0.5-1					
OTR (23° C , 0% RH)	ASTM D3985	cc/m²/day	-	0.5-1					

MD: Machine direction, TD: Transverse direction

Storage and Handling :	<b>PETMET</b> need to be stored in a closed place and should be prevented to expose to direct sunlight or light sources. It is recommended to store at conditions not exceeding 35 C and in relative humidity less than 60%.
Food Contact :	This film complies with the EU and FDA regulations. Specific documents are available upon request.
Disclaimer :	PETCO does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped. NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore PETCO denies any responsibility for any loss or damage that may occur from the use of this information. PETCO strongly suggests that before any vast usage, make sure to study "Customer's Guide" and test our product in limited amounts.

Head Office: No.6; Riahi St.; Karaj Makhsous Road; Azadi sq.; Tehran; Iran, Postal Code: 1391947611 Central Tel: +98 (0)21 44 63 44 00-7, Sales Tel/Fax: +98(0)21 44 64 02 24 , Marketing Tel:+98 (0)21 44 65 71 93

## **Metallized BOPET Film**