
**Matt BOPET Film** 



## PETPAK 253S

Features:

- One side matt film with medium gloss
- Superior mechanical strength
- Excellent machinability
- Chemical coated side provide excellent adhesion to wide range of inks and adhesives
- Excellent flatness and dimensional stability



Application:

 Matt film for flexible packaging; applicable in printing and lamination.

 This film is recommended for processes with high heat tension like sterilization and pasteurization applications.

| Specification                         | Test Method | Unit      | Test Direction | 12μ   |
|---------------------------------------|-------------|-----------|----------------|-------|
| Yield                                 | ASTM D4321  | m²/Kg     | -              | 59.5  |
| Wetting Tension                       | ASTM D2578  | Dyne/cm   | Coated Side    | 48-50 |
|                                       |             |           | Matt Side      | 42-44 |
| Tensile Strength                      | ASTM D882   | N/mm²     | MD             | 190   |
|                                       |             |           | TD             | 200   |
| Elongation at Break                   | ASTM D882   | %         | MD             | 130   |
|                                       |             |           | TD             | 100   |
| Thermal Shrinkage<br>(150 °C, 30 min) | ASTM D1204  | %         | MD             | 2     |
|                                       |             |           | TD             | 1     |
| Haze                                  | ASTM D1003  | %         | -              | 48    |
| Gloss                                 | ASTM D2457  | %         | Glossy Side    | 75    |
|                                       |             |           | Matt Side      | 45    |
| Dynamic C.O.F                         | ASTM D1894  | -         | Matt-Matt      | 0.35  |
|                                       |             |           | Matt-Metal     | 0.25  |
| WVTR (38° C , 90% RH)                 | ASTM F 1249 | g/m²/day  | -              | 45    |
| OTR (23° C , 0% RH)                   | ASTM D 3985 | cc/m²/day | -              | 130   |

MD: Machine direction, TD: Transverse direction

Storage and Handling : PETPAK need to be stored in a closed place and should be prevented to expose to direct sunlight or light sources. It is recommended to store at conditions not exceeding 35 °C and in relative humidity less than 60%.

Food Contact :

This film complies with the EU and FDA regulations. Specific documents are available upon request.

Disclaimer :

PETCO does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped. NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore PETCO denies any responsibility for any loss or damage that may occur from the use of this information. PETCO strongly suggests that before any vast usage, make sure to study "Customer' s Guide " and test our product in limited amounts.

## Head Office: No.6; Riahi St.; Karaj Makhsous Road; Azadi sq.; Tehran; Iran, Postal Code: 1391947611 Central Tel: +98 (0)21 44 63 44 00-7, Sales Tel/Fax: +98(0)21 44 64 02 24, Marketing Tel:+98 (0)21 44 65 71 93