Technical Data Sheet •



POLABLE 142 E

Both sides treated, one side matt and one side printable

Pearlized BOPP film

Features: Excellent opacity, gloss and stiffness Less orange peel effect after injection molding

- Less orange peel effect after injection molding
 Improved slip and anti-static characteristics
- for sheeting and die cutting
- High adhesion skin layer provides excellent adhesion with solvent based, conventional offset inks

Application: High stiff BOPP film for in- mold labeling, suitable for sheet -fed and roll-fed printing, It can be used instead of CPP IML films for rather big containters.Yet suitability of film for container size must be checked at first. This film can be used for other kinds of applications such as self adhesive labels (SAL), cut & stack.







Specification	Test Method	Unit	Test direction	60 µ	70 µ
Wetting Tension	ASTM D 2578	Dyne/cm	Ν	≥ 38	
			Т	≥ 38	
Tensile Strength	ASTM D 882	N/mm²	MD	80	
			TD	185	
Elongation at break	ASTM D 882	%	MD	150	
			TD	40	
Thermal Shrinkage *	ASTM D 1204	%	MD	≤ 4	
			TD	≤ 2	
Gloss	ASTM D 2457	%	т	80	
Opacity	DIN 53146	%	-	70	75
Yield	ASTM D 4321	m²/kg	-	23.8	20.4
Unit weight	ASTM D 4321	gr/m²	-	42	49
Density	ASTM D 1505	gr/cm ³	-	0.70	
Dynamic C.O.F	ASTM D 1894	-	N-N	0.4	
			film - metal	0.3	

F: Film roll out- side, N: Film roll in- side, MD: Machine direction, TD: Transverse direction

*(120 °C, 5 min)

Available thicknesses: All thicknesses between 60 - 70 µm can be produced upon request.

One side treated film (Polable 141 E) can be produced upon request.

This film complies with the EU and FDA regulations. Specific documents are available upon request.

Polfilm does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped.

NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polfilm denies any responsibility for any loss or damage that may occur from the use of this information.

Polfilm strongly suggests that before any vast usage, make sure to study "Customer's Guide " and test our product in limited amounts.

Head Office: No.6 Riahi St. Karaj Makhsous Road, Azadi Sq. Tehran-Iran, Postal Code:1391947611 Central Tel: +98 (0)21 44 63 44 00-7, Sales Tel/Fax: +98 (0)21 44 64 02 24