


- Features: Excellent opacity, gloss and stiffness
 Orange peel effect after blow molding
 - Improved slip and anti-static characteristics
 - for sheeting and die cutting

Special skin layer provides excellent adhesion with different kind of inks

Application: High stiff BOPP film for blow mold labeling, suitable for sheet -fed and roll-fed printing.



Specification	Test Method	Unit	Test Direction	105 μ
Wettingtension	ASTM D 2578	Dyne/cm	Treated Side	≥36
Tensile Strength	ASTM D 882	N/mm²	MD	75
			TD	140
Elongation at break	ASTM D 882	%	MD	145
			TD	50
Thermal Shrinkage	ASTM D 1204	%	MD	≤4
			TD	≤2
Gloss	ASTM D 2457	%	-	23
Density	ASTM D1505	gr/m³	-	0.73
Yield	ASTM D 4321	m²/kg	-	13
Opacity	DIN 53146	%	-	80
Dynamic C.O.F	ASTM D 1894	-	Film - Film	0.3
		-	Film - Metal	0.25

MD: Machine direction, TD: Transverse direction

This film complies with the EU and FDA regulations. Specific documents are available upon request.

denies any responsibility for any loss or damage that may occur from the use of this information.

Polfilm does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped. NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polfilm

Polfilm strongly suggests that before any vast usage, make sure to study "Customer's Guide" and test our product in limited amounts.

Head Office: No.6 Riahi St. Karaj Makhsous Road, Azadi Sq. Tehran-Iran, Postal Code:1391947611 Central Tel: +98 (0)21 44 63 44 00-7, Sales Tel/Fax: +98 (0)21 44 64 02 24

Date: 30.04.2022