
Technical Data Sheet •



| Specification | Test Method | Unit | Test Direction | 57 μ |
|---------------------|-------------|---------|----------------|-------|
| Wettingtension | ASTM D 2578 | Dyne/cm | Treated Side | ≥38 |
| Tensile Strength | ASTM D 882 | N/mm² | MD | 120 |
| | | | TD | 240 |
| Elongation at break | ASTM D 882 | % | MD | 200 |
| | | | TD | 40 |
| Thermal Shrinkage | ASTM D 1204 | % | MD | ≤4 |
| | | | TD | ≤2 |
| Gloss | ASTM D 2457 | % | Glossy Side | 50 |
| Density | ASTM D1505 | gr/cm³ | - | 0.95 |
| Yield | ASTM D 4321 | m²/kg | - | 18.29 |
| Opacity | DIN 53146 | % | - | 80 |
| Dynamic C.O.F | ASTM D 1894 | - | Matt - Matt | 0.35 |
| | | - | Matt - Metal | 0.25 |

MD: Machine direction, TD: Transverse direction

Available thicknesses: All thicknesses between 45 - 57 μm can be produced upon request.

Non-coated type of this film (Polable 132 LIV) can be produced upon request.

Polfilm does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped. NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polfilm denies any responsibility for any loss or damage that may occure from the use of this information.

Polfilm strongly suggest that before any vast usage, make sure to study "Customer's Guide" and test our product in limited amounts.

Head Office: No.6 Riahi St. Karaj Makhsous Road, Azadi Sq. Tehran-Iran, Postal Code:1391947611 Central Tel: +98 (0)21 44 63 44 00-7, Sales Tel/Fax: +98 (0)21 44 64 02 24

www.polfilm.net